

BLACKBUTT

Other Names: Coastal Blackbutt, Pink Blackbutt, Eucalyptus Pilularis


Origins

Eastern Australia

Description


Blackbutt is part of the eucalyptus Genus as such its growth rate would be considered rapid. The texture of the timber is even, generally straight as such making it simple for interior applications.

The heartwood is from a golden yellow to brown with a slight pinkish presence.




SUSTAINABILITY

The Eucalyptus pilularis/ Blackbutt is plantation grown and will reach maturity within an average of 15 years which is considered a very fast growth rate. With the fast growth rate it makes the timber easily sustained.



APPLICATION

Blackbutt's timber is widely used for structural applications, exterior and interior decorations. In Eastern Australia it is commonly used for cladding, internal flooring, decking and furniture.



MECHANICAL PROPERTIES

Durability: Class 1

Density: 880 kg/m³

BAL Rating: 12.5 / 19 / 29

Termite resistant: Yes

Lycid Borer Susceptible: No

Tannin Leach: Moderate

Origin: NSW / QLD

